



COATINGS

Loctite offers a variety of coatings to protect, seal, insulate, prevent corrosion, colour code and add gripping power. Many products provide excellent resistance to acids, alkalis, salt and moisture that can damage equipment.

Colour Guard® Tough Rubber Coating

Inhibits rust and corrosion; seals, insulates and identifies almost any material in minutes. Creates a non-slip gripping surface. Rubber coating won't crack or chip. Acid and alkali resistant. Lasts for years. Use to 200°F. Dip, spray or brush to apply. Suggested applications include: tools, metal, electrical connections, masonry, wood, conveyors, glass, rope, fabric.

Extend® Rust Treatment

One-step rust treatment goes on white and converts rust to a durable, black, metal-protective coating in 10 minutes. Wirebrush parts and apply with brush or spray. Surface rust must be present. Use as a primer or finish coat. Resists temperatures to 250°F intermittent, 200°F continuous.

Maxi-Coat

Heavy duty coating provides long-term protection for metal parts, equipment and machinery. Forms a protective, waxy film which seals out moisture, air, acid and other corrosive elements. Great for protecting parts in storage. Removable.

Cold Galvanizing Compound

Sprays on metal surfaces to prevent corrosion even when surface is scratched. Ideal touch-up for welded seams. Highly resistant to salt corrosion and water. Not resistant to acid or alkaline solutions. Contains no ozone-depleting compounds.

Product	Spaenaur No.	Mfr. No.	Container	Coating Appear.	Coating Thick.	Drying Time	Temp. Resist.	Moisture Resist.	Salt Spray Test	Accelerated Weather Test
Color Guard® Tough Rubber Coating	800-103	34979	14.5 fl. oz. can	Black	1 dip:	4 hours (allow 30 minutes between)	-30°F to 200°F	Excellent/ ASTM E-96	Passed 1000 hours/ ASTM B-117	10 years with slight loss of thickness/ ASTM G-53-84
	800-225	34980	1 gal. can	Black	8-10 mil					
	800-104	34982	14.5 fl. oz. can	Blue	1 Spray:					
	800-279	34983	1 gal. can	Blue		3-5 mil				
	800-114	34985	14.5 fl. oz. can	Red						
	800-226	34986	1 gal. can	Red						
800-125	34988	14.5 fl. oz. can	Yellow							
800-227	34989	1 gal. can	Yellow							

Product	Spaenaur No.	Mfr. No.	Container	Coating Appearance	Drying Time	Temp. Resistance	Key Spec.
Extend® Rust Treatment	800-088	30539	10.5 oz. net wt. aerosol	Converts from a white liquid to a black coating	30 minutes to touch	Up to 250°F (121°C)	-
	800-130	75430	1 qt. bottle				
	800-228	75448	1 gal. bottle				
	800-229	75465	5 gal. pail				
Maxi-Coat	800-400	51211	16 oz. net wt. aerosol	Yellow/off White	1-2 hours	Up to 200°F (93°)	-
Cold Galvanizing Compound	800-089	82039	15 oz. net wt. aerosol	Low gloss grey	15 min. to touch	Up to 400°F continuous; 600°F intermittent	Conforms to MIL-P-26915A Conforms to MIL-T-26433 Conforms to MIL-T-21035 Conforms to MIL-P-46105 Conforms to ASTM A239-41

CATALOG 13

Bold Type Spaenaur No's. in Stock.
Light Type Spaenaur No's. available upon request.

Tel: 1-800-265-8772 Fax: 519-744-0818

Q11